SCHOMBURG GmbH & Co. KG Aquafinstrasse 2 - 8 D-32760 Detmold (Germany)

phone +49-5231-953-00 fax +49-5231-953-108

email export@schomburg.de www.schomburg.com







Technical Data Sheet

BETOCRETE®-CP-360-WP

Art.-No. 2 06446

Crystalline waterproofing admixture with hydrophobic effects



NPD = "No Performance Determined"

BETOCRETE-CP360 -WP is powder-based admixture for designing a water tight concrete with innovative 2 in 1 technology. Initially it functions chemically and reduces the water absorption in the matrix. In the next step, nanoscale crystals are formed in the capillary system by special active catalysts, which become active on contact with water. This forms a concrete which is sustainable and permanently impermeable to water.

- Powder based
- Innovative 2 in 1 technology
- Crystallization of the capillaries
- Reduces capillary absorption
- Crack healing possible for penetrating cracks up to 0.4 mm and for map/pattern cracks up to 0.5 mm
- Reduction in Chloride migration
- Improvement of the resistance to freeze/thaw
- Minimization of maintenance and repair costs
- Time saving

Areas of application:

BETOCRETE-CP-360 -WP can be applied to all concrete where water penetration should be permanently prevented.

These are for example: Cooling towers at power stations, tanks and containers, retaining basins, swimming pools, parking garages, parking lot levels, foundations, sandwich units, waterproof concrete, sewer channels/manhole access points, tunnels, concrete pipes and everywhere, where watertightness is needed.

Technical data:

Colour: grey
Consistency: Powder
Bulk density: 0.80 g/cm³
Application temp.: +5 °C

Storage: dry, 12 months in the original

unopened container. Use opened containers promptly

Packaging: 17 kg bag

Water pollution class: 1 (Self classification)

Concrete requirements:

Minimum cement content: CEM I 270 kg/m³

CEM II 290 kg/m³ CEM III /A 380 kg/m³

Pozzolanic cement with

pozzolan content >20%: 300 kg/m³ Granulated slag: max.100 kg/m³ Fly ash: max. 80 kg/m³

Product preparation:

Dosage:

The required dosage rate is 0.75 - 1.25% based on CEM weight and is dependent, amongst other criteria, on the concrete formula and the reactivity of the cement. The dosage is to identify with a suitability trial. The following dosage levels have stood the test of time:

w/c value < 0.4 0.75 % based on CEM > 0.4-0.5 0.80 % based on CEM

> 0.4-0.5 0.80% based on CEM > 0.5-0.55 0.90% based on CEM

Do not exceed the maximum dosage level of 1.25 %

based on CEM weight.

2 10/17

BETOGRETE®-CP-360-WP

Dosage at concrete plants:

BETOCRETE-CP-360-WP is to be dosed into the aggregate and mixed for a minimum of 30 seconds before adding the water and cement. Subsequently mix for a minimum of 45 seconds until ready for use.

Dosage in concrete trucks:

BETOCRETE-CP-360-WP is dosed directly into the mixing drum of the concrete truck on the building site. The mixing time should be 1 min/ m^3 of drum contents but be a minimum of 5 minutes.

Advice:

- Dependent on composition, concrete modified with BETOCRETE-CP-360-WP can feature crystals on the surface of the concrete.
- Carry out preliminary trials in accordance with current standards before using BETOCRETE-CP-360-WP or other types of additives.
- Lignite fly ash is only suitable with restrictions.
- The use of CEM III/B&C cements is excluded.
- The prescribed crack width restrictions given by the Planner/Engineer/Structural Engineer must be respected in all circumstances. Differing interpretations are to be proven with relevant design verification and design suitability.
- Concrete with BETOCRETE-CP-360-WP must be produced, installed and cured following current valid standards.
- In rare circumstances BETOCRETE-CP-360-WP may influence the initial set of the concrete. As a system compatible product, RUXOLITH-T5 (VZ) is available to control the concrete.

Please observe a current valid EU safety data sheet!

2 TB/CoS/TM 10/17